

*“A Reliable
and Responsive
Adhesive
Company.”*

Bondfilm™ 8310 is a glass fabric supported thermally conductive film adhesive. It is formulated to bond materials with mismatched coefficient of thermal expansion. It also offers a controlled bondline thickness.

Adhesive Properties

Color:	Cream
Work Life @ 25°C:	10 days
Cure Options:	30 minutes @ 150°C or 2 hours @ 125°C
Service Temperature Range:	-40°C to 150°C
Lap Shear Strength @ 25°C (Al to Al):	3500 psi
@ 25°C (Au to Au):	2000 psi
Glass Transition Temperature (T _g):	59°C
Specific Heat:	1.48 J/gK
Thermal Diffusivity:	.0029 cm ² /s
Thermal Conductivity:	0.80 W/mK
Weight Loss @ 300°C:	0.42%
Coefficient of Thermal Expansion:	
Below T _g :	65 x 10 ⁻⁶ in/in/°C
Above T _g :	299 x 10 ⁻⁶ in/in/°C
Shelf Life:	1 year @ -40°C 6 months @ 5°C

Adhesive properties are not intended to be used as specification limits.

Bondline™
Electronic Adhesives, Inc.

756 N. Pastoria Avenue, Sunnyvale, CA 94085 USA
Phone: 408-830-9200 Fax: 408-830-9266 Website: www.bondline.net

Rev. 02/04/04

INSTRUCTIONS:

Place film adhesive between surfaces to be bonded. Apply continuous pressure of 1-5 psi during cure, using weight or spring loaded clamp.

AVAILABILITY:

Bondfilm™ 8310 epoxy film is available in sheet stock and die cut preforms. Die cut preforms are cut to customer specifications. Width and length tolerances are $\pm .005$ inch. Thickness tolerance $\pm .001$ inch.

STORAGE LIFE:

Storage life of sheet stock is 10 days, when stored at room temperature. Storage life is 1 year at -40°C or colder. Die cut preforms require storage at 5°C or colder. At 5°C, storage life is 6 months.

CAUTION: For industrial use only. People with sensitive skin may have a reaction to this adhesive. Avoid skin contact. Wash all areas with soap and water immediately if contact does occur. It is important to refer to Material Safety Data Sheet (MSDS) OSHA for more details.

Bondline™
Electronic Adhesives, Inc.

756 N. Pastoria Avenue, Sunnyvale, CA 94085 Phone: 408-830-9200 Fax: 408-830-9266 Website: www.bondline.net

© Bondline Electronic Adhesives, Inc. All rights reserved. All trademarks and registered trademarks belong to their respective owners. Notice to User: The information contained herein is based on technical data and tests which we believe reliable. It should be used by persons who have technical skill, at their own discretion and risk. Since conditions of use are outside of Bondline's control, we can assume no liability of results obtained or damages incurred through the application of data presented. Bondline's sole liability is limited to refund of purchase price of any product shown to be defective.