

*“A Reliable  
and Responsive  
Adhesive  
Company.”*

Bondfilm™ 8366 is a glass fabric supported thermally  
conductive flexible film adhesive. It is formulated to bond  
materials with mismatched coefficient of thermal  
expansion. It also offers a controlled bondline thickness.

#### Adhesive Properties

Color:	Cream
Work Life @ 25°C:	24 hours
Cure Options:	1 hour @ 150°C or 2 hours @ 125°C or 4 hours @ 100°C
Service Temperature Range:	-40°C to 150°C
Lap Shear Strength @ 25°C (Al to Al):	1500 psi
@ 25°C (Au to Au):	1500 psi
Glass Transition Temperature (Tg):	29°C
Thermal Conductivity:	0.8 W/mK
Weight Loss @ 300°C:	0.63 %
Weight Loss upon cure:	0.82 %
Coefficient of Thermal Expansion:	
30°C to 100°C:	129 x 10 <sup>-6</sup> in/in/°C
Shelf Life:	1 year @ -40°C

Adhesive properties are not intended to be used as specification limits.

***Bondline***™  
*Electronic Adhesives, Inc.*

756 N. Pastoria Avenue, Sunnyvale, CA 94085 USA  
Phone: 408-830-9200 Fax: 408-830-9266 Website: www.bondline.net

Rev.02/02/04

---

**INSTRUCTIONS:**

Place film adhesive between surfaces to be bonded. Apply continuous pressure of 1-5 psi during cure, using weight or spring loaded clamp.

---

**AVAILABILITY:**

Bondfilm™ 8366 epoxy film is available in sheet stock and die cut preforms. Die cut preforms are cut to customer specifications. Width and length tolerances are  $\pm .005$  inch. Thickness tolerance  $\pm .001$  inch.

---

**STORAGE LIFE:**

Storage life is 1 year at -40°C or colder.

**CAUTION:** For industrial use only. People with sensitive skin may have a reaction to this adhesive. Avoid skin contact. Wash all areas with soap and water immediately if contact does occur. It is important to refer to Material Safety Data Sheet (MSDS) OSHA for more details.

***Bondline***™  
*Electronic Adhesives, Inc.*

756 N. Pastoria Avenue, Sunnyvale, CA 94085 Phone: 408-830-9200 Fax: 408-830-9266 Website: [www.bondline.net](http://www.bondline.net)

---

© Bondline Electronic Adhesives, Inc. All rights reserved. All trademarks and registered trademarks belong to their respective owners. Notice to User: The information contained herein is based on technical data and tests which we believe reliable. It should be used by persons who have technical skill, at their own discretion and risk. Since conditions of use are outside of Bondline's control, we can assume no liability of results obtained or damages incurred through the application of data presented. Bondline's sole liability is limited to refund of purchase price of any product shown to be defective.